

## Product data sheet

1/1

Denomination of the product  
Customer product designation  
Issue / Version

**NEGOZONE 3457 M**

1 / 08/08/11

### Typical product data

Analysis	Method	Unit	Typical
Congealing point	DIN ISO 2207	°C	68.0
Needle penetration 25 °C	DIN 51 579	mm/10	17
Kin. viscosity 100 °C	DIN 51562 P. 1	mm <sup>2</sup> /s	8.5
Density 80 °C	DIN 51 757 method 4	kg/m <sup>3</sup>	782.0
Content of oil	DIN ISO 2908	% w/w	0.6
Colour Saybolt	Dr. Lange	-	28

The above mentioned data are only an indication and do not represent any guarantee. Any deviations of the data are no reason for claim.