

Product data sheet

1/1

Denomination of the product **PIONIER 2901**
White Vaseline Ph.Eur./USP

Customer product designation
Issue / Version 1 / 30/06/11

Typical product data

Analysis	Method	Unit	Typical
Congealing point	DIN ISO 2207	°C	54.0
Drop Point	ASTM D 3954	°C	59.0
Drop Point	Ph. Eur. 2.2.17	°C	58.0
Drop Point	USP 34 / NF 29	°C	58.0
Drop Point	ASTM D 127	°C	59.0
Cone penetration 25 °C	DIN 51 580	mm/10	160.0
Cone penetration 25 °C	Ph. Eur. 2.9.9	mm/10	160.0
Cone penetration 25 °C	USP 34 / NF 29	mm/10	160.0
Kin. viscosity 100 °C	DIN 51562 P. 1	mm ² /s	6.4
Colour Lovibond (yellow)	IP 17 B (2")	-	0.6
Colour	DIN ISO 2049	-	< 0.5
Colour	sensitive		white
Purity	USP 34 / NF 29		conform
Purity	Latest Edition Ph. Eur.		conform

The above mentioned data are only an indication and do not represent any guarantee. Any deviations of the data are no reason for claim.