

NEGOZONE[®] 220

Anti Ozonant Wax

			NEGOZONE [®] 220
	Unit	Method	
Colour Saybolt	-	ASTM 156	28
Viscosity at 100°C	mm ² /s	ASTM D 445	6,7
Congealing point	°C	ASTM D 938	66
Needle penetration at 25°C	1/10mn	ASTM D 1321	15
Oil content	wt.	DIN ISO 2908	0,8

Data are subject to usual tolerances

Stand: 25.09.2007