

Process Oils / Plasticizing Oils, light

Paraffinic

TUDALEN®	Colour	Aniline Point °C	Carbon Structure			V.G.C.	Refractive Index 20 °C	Density kg/m ³ 15 °C	Flash Point COC °C	Pour Point °C	Cin. Viscosity		Polycyclic Arom. Hydrocarbons wt. %
			wt. % CA%	CN%	CP%						mm ² /s 40 °C	100 °C	
DIN	ISO 2049	ISO 2977	51 378-U			51 378	51 423 B.2	51 757 T.1	ISO 2592	ISO 3016	51 562 T.1		IP 346

Typical values

B 8013 EXTRA	1,5	115	2	32	65	0,810	1,4830	880,0	256	- 12	96,0	10,5	
B 8014 EXTRA	1,0	117	1	32	67	0,806	1,4810	877,0	250	- 12	97,0	10,9	< 1,0
C-130	< 1,0	123	2	30	68	0,805	1,4880	889,0	292	- 12	250,0	20,0	0,1
C-830	7,0	-	6	27	67	-	1,4965	903,0	240	- 15	601,0	35,0	-
4153	< 3,5	124	5	28	67	-	1,4960	905,0	306	< - 12	680,0	35,8	< 2,0

Data are subject to usual tolerances.

Klaus Dahleke KG
Am Sandtorkai 64
D-20457 Hamburg

Tel. +49 (40) 432 18-0
Fax +49 (40) 432 18-400
Email hur@hansen-rosenthal.de

Date: 20.12.2005